



# LATAPOXY<sup>®</sup> 2000 Industrial Epoxy Grout

Data Sheet 634.0

## 1. PRODUCT NAME

LATAPOXY<sup>®</sup> 2000 Industrial Epoxy Grout

## 2. MANUFACTURER

LATICRETE International, Inc.

1 LATICRETE Park North

Bethany CT 06524-3423 USA

Telephone: (203) 393-0010 ext. 235

Toll Free: (800) 243-4788 ext. 235

FAX: (203) 393-1684

Fax on Demand: (800) 359-3297

Internet: www.laticrete.com

## 3. PRODUCT DESCRIPTION

LATAPOXY<sup>®</sup> 2000 Industrial Epoxy Grout is a highly chemical resistant industrial grade epoxy grout for: ceramic tile, pavers, floor brick, packing house tile and stone. LATAPOXY 2000 Industrial Epoxy Grout is supplied as factory proportioned kits consisting of epoxy resin, hardner, and chemical resistant silica filler.

**Usage** - Use in corrosive environments such as:

**Industrial** - bakeries, dairies, cheese factories, breweries, CIP rooms, meat packing plants, soft drink plants, confectioneries, canneries, distilleries, pharmaceutical factories.

**Commercial** - institutional kitchens, fast food restaurants, cafeterias, laboratories, supermarkets.

### Advantages

- High chemical resistance
- Improved temperature resistance
- Highly resistant to bacteria attack
- Maximum physical strength
- Water cleanable
- Fast curing
- Cures at low temperature
- Meets USDA & USFDA requirements
- Exceeds ANSI 118.3-1999 (Epoxy) and ANSI 118.5-1999 (Furan) performance requirements

### Packaging

Pail #2 size

Unit Net Weight: 24.2 lbs. (10.9 kg)

Unit Volume: 1.8 gals. (6.8 liters)

Carton #4 Size

Unit Weight: 50.4 lbs. (22.8kg)

Unit Volume: 3.6 gals. (13.6 liters)

Note: #2 and #4 units also available in separate components, liquids only and Part C Filler Powder

Colors: Standard Colors: grey and black, Custom colors available on request.

**Shelf Life** - Factory sealed containers of this product are guaranteed to be of first quality for two (2) years.

### Limitations

- Maximum chemical resistance is achieved in seven (7) days at 70°F/21°C. Protect from exposure to strong chemicals until fully cured; at colder temperatures it takes longer to achieve full cure.
- Grouts for ceramic tile, pavers, brick and stone are not replacements for waterproof membranes. When a

waterproof membrane is required, use LATICRETE Waterproof Membrane.

- Not for use with Bright White or light colored grouts. LATAPOXY 2000 Part C Filler Powder best used with the following grout colors: 04, 06, 07, 08, 11, 12, 14, 15, 22, 24, 25, 28, 30, 34, 35, 42, 46, 92, 71, 72, 76.

### Cautions

- Protect finished work from chemical exposure, dirt and traffic until fully cured.
- Until cured, LATAPOXY 2000 industrial Epoxy Grout may irritate eyes and skin. Avoid contact with eyes and or prolonged contact with skin. In case of contact, flush thoroughly with water.
- Do not take internally. Silica sand may cause cancer or serious lung problems. Avoid breathing dust. Wear a respirator in dusty areas.
- Keep out of reach of children.

## 4. TECHNICAL DATA

### Applicable Standards

- ANSI A118.3-1999, ANSI A118.5 - 1999 (American)
- BS 5980-1999 Type 5 Class AA (British)

### Performance Properties

EVALUATION PER ANSI A118.3-1999		
PROPERTY	VALUE	
TEST/ NO.	EVALUATION	REQUIREMENT
Water Cleanability (E5.1)	Pass	80 min.
Initial Setting Time (E5.2)	Pass	> 2.0 hrs.
Service Setting Time (E5.2)	Pass	< 7 days
Shrinkage (E5.3)	0.07%	< 0.25%
Sag (E5.4)	Pass	no change
Quarry Shear Bonds (E5.5)	1000 PSI (6.9MPa)*	> 1000 psi (6.9 MPa)
Compressive Strength (E5.6)	15500 PSI (107 MPa)	> 3500 psi (24 MPa)
Tensile Strength (E5.7)	2600 PSI (18MPa)	> 1000 psi (6.9 MPa)
Thermal Shock (E5.8)	500 PSI (3.4MPa)	> 500 psi (3.4 MPa)

\*=Tile Failed During Test

EVALUATION PER ANSI A118.5 - 1999			
Property	Test Method	Evaluation	Grout Requirement Silica
Compressive Strength	ASTM C579	14700 PSI (101 MPa)	3000 psi (21 MPa)
Tensile Strength	ASTM C307	2577 PSI (17.7 MPa)	400 psi (2.75 MPa)
Absorption	ASTM C413	0.16%	Max. 1%
Modulus of Rupture	ASTM C580	5300 psi (37 MPa)	600 psi (4.1 MPa)
Initial Set, Hours	ASTM C308	4	Max 5
Final Set, Days	ASTM C308	2	Max 7
Linear Shrinkage	ASTM C531	0.27%	Max. 1%
Working Time Minutes	ASTM C308	35	Min. 10
Bond Strength	ASTM C321	Pass*	150 psi (1 MPa)

\*=Brick Failed During Test

Data Sheets are subject to change without notice, for latest revision check our website.

LDS6340/MTB/Rev.06/27/03

SERVICE TEMPERATURE RANGE**	
Intermittent Exposure	up to 360°F/182°C
Constant Exposure	up to 185°F/80°C

\*\*Service Temperature Exposure defined as: **Intermittent** - where hot materials, liquids or steam come in contact with grout for a short time.

**Constant** - where grout is subjected to continuous heat such as under a bakery oven.

### Working Properties (70°F(21°C))

Working Time	35 minutes
Wet Density	112 lbs/ft <sup>3</sup> (1800 kg/m <sup>3</sup> )

### Time to Traffic

CURE TIME			
FLOOR TEMPERATURE	TIME TO LIGHT TRAFFIC*	TIME TO HEAVY TRAFFIC**	FULL CURE***
40°F(4°C)	24 Hours	48 Hours	7 Days
50°F (10°C)	20 Hours	32 Hours	7 Days
60°F (16°C)	16 Hours	24 Hours	7 Days
70°F (21°C)	5 Hours	10 Hours	5 Days
80°F(27°C)	4 Hours	7 Hours	1 Day
90°F(32.2°C)	2 Hours	3 Hours	12 Hours

\* Foot Traffic \*\* Place Equipment \*\*\* Exposure to Chemical and Heat

Chemical Resistance* Chart			
Chemical Name	Continuous Exposure	Inter-mittent Exposure	Splash Exposure
<b>Food Acids</b>			
Lactic to 10 %	R	R	R
Acetic to 10%	R	R	R
Formic to 5 %	R	R	R
Citric to 50%	R	R	R
Tartaric to 50%	R	R	R
Tannic to 50%	R	R	R
Oleic to 100%	R	R	R
Phosphoric to 80%	R	R	R
<b>Mineral Acids</b>			
Hydrofluoric acid** 10%		R	R
Sulfuric to 50%**	R	R	R
Nitric to 30%**	R	R	R
Hydrochloric to** 36.5%	R	R	R
<b>Corrosive Cleaners</b>			
Sodium Hypochlorite** (Bleach) 3%	R	R	R
Sodium Hydroxide (Saturated)	R	R	R
<b>Solvents</b>			
Xylene	R	R	R
Ethyl Alcohol	R	R	R
Mineral Spirits	R	R	R
Toluene	R	R	R
Methylene Chloride	NR	NR	NR
Gasoline	R	R	R

\*Chemical Resistance defined as:

**Splash** - minor spill wiped up quickly such as in a laboratory.

**Intermittent** - Exposure to chemicals where clean up takes place several times a day such as in a commercial kitchen.

**Continuous** - heavy exposure to chemicals where clean up is less frequent such as in an industrial food plant.

**R=Recommended, NR=Not Recommended.** Chemical Resistance determined in accordance with ASTM C267-1999.

\*\* Long Exposure will cause color change.

Specifications subject to change without notification. Results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

## 5. INSTALLATION

### Surface Preparation

Before starting to grout remove spacers and debris in grout and remove dust and dirt using a damp sponge. Do not leave water standing in joints.

Do not clean tiles with acid cleaners. Substrate temperature must be between 45°F(7°C) and 90°F(32°C).

**Note:** Temperature will effect working properties of LATAPOXY 2000 Industrial Epoxy Grout. Warm temperatures will speed curing and shorten working time. Cool temperatures will slow curing and require longer time to traffic. Store LATAPOXY 2000 Industrial Epoxy Grout at 70°F(21°C) for 24 hours prior to use.

**Mixing** - Pour LATAPOXY 2000 Industrial Epoxy Grout Part A and Part B into a clean mixing pail and mix thoroughly by hand or with a slow speed mixer (<300 RPM) until liquids are completely blended.

**Note: For vertical installations add Part D at this time.** Add LATAPOXY 2000 Part C Filler Powder and mix until uniformly blended.

**Application** - Immediately pour entire contents of pail onto a flat surface (Do Not Leave in Pail). Spread with a sharp, firm rubber grout float. Work the grout paste into the joints until completely filled. Use diagonal strokes to pack the joints. Insure that joint is filled and grout is not just sitting on top (i.e. "bridging the joint").

**Cleaning** - Remove excess grout from the face of the tiles with the edge of the grout float. Hold the float at a 90° angle and pull it diagonally across the joints and tile to avoid pulling out the material. Clean using a white nylon pad and plenty of cool, clean water. For detailed application instructions and coverage information refer to Data Sheet 631.5.

## 6. AVAILABILITY AND COST

### Availability

LATICRETE and LATAPOXY® materials are available worldwide. For distributor information, call:

Toll Free: (800) 243-4788

Telephone: (203) 393-0015

For on-line distributor information, visit LATICRETE at [www.LATICRETE.com](http://www.LATICRETE.com).

**Cost** - Contact a LATICRETE Distributor in your area.

## 7. WARRANTY

LATICRETE International, Inc. warrants that LATAPOXY 2000 Industrial Epoxy Grout is free from manufacturing defects and will not break down, deteriorate or disintegrate under normal usage for a period of one (1) year from date of purchase subject o the terms and conditions stated in Data Sheet 230.13 LATICRETE Product Warranty (see 10. FILING SYSTEM).

## 8. MAINTENANCE

LATICRETE and LATAPOXY grouts require routine cleaning with a neutral pH soap and water. All other LATICRETE and LATAPOXY materials require no maintenance but installation performance and durability may depend on properly maintaining products supplied by other manufacturers.

## 9. TECHNICAL SERVICES

### **Technical assistance**

Information is available by calling the LATICRETE Technical Service Hotline

(hours 8:00 AM to 5:30 PM EST):

Toll Free: (800) 243-4788 ext. 235

Telephone: (203) 393-0015 ext. 235

FAX: (203) 393-1948

### **Technical and safety literature**

To receive data via fax 24 hours 7 days, call:

- (800) 359-3297 or (203) 393-0015, ext. 360
- To receive a Material Safety Data Sheet, enter Fax on Demand code 8045

## 10. FILING SYSTEM

Additional product information available upon request:

DS 633.0: LATAPOXY 300 Epoxy Adhesive  
(Fax on Demand Code 6330)

DS 230.13: LATICRETE Product Warranty  
(Fax on Demand Code 3013)



***Globally proven.  
Professionally endorsed.***

### **LATICRETE INTERNATIONAL, INC.**

1 LATICRETE PARK NORTH • BETHANY, CT 06524-3423 USA

TEL: (203) 393-0010 • (800) 243-4788

FAX: (203) 393-1684 • FAX ON DEMAND: (800) 359-3297

**www.laticrete.com • support@laticrete.com**

**LATICRETE MIDDLE EAST** Tel: (971) 7 244 6396 Fax: (971) 7 244 5915

**LATICRETE ASIA PACIFIC** Tel: (65) 6262-4237 Fax: (65) 6262-3701

**LATICRETE EUROPE** Tel: (34) 966 491 908 Fax: (34) 966 491 909

**LATICRETE LATIN AMERICA** Tel: (203) 393-0010, EXT. 218 Fax: (203) 393-1684

©2003 LATICRETE INTERNATIONAL, INC.

Data Sheets are subject to change without notice; for latest revision check our website.

LDS6340/MTB/Rev.06/27/03